

New Natural Stone-like Decorative Coating

GRANI PALACE

グラニパレス






GRANI PALACE is a new type of luxurious decorative coating, with layers of inorganic natural stone mid-coat and multi-coloured main coat. A magnificent appearance can be achieved with Bush hummer, Travertine, and Tail finishes. Also, its acrylic silicon resin paint film successfully performs high durability and super dirt-resistance.



Decorative Design

It creates magnificent walls with stone-like surfaces. The various designs help you create unique space of your own.



Super Dirt-resistance

Super dirt-resistant topcoat through our original ceramic multiple technology keeps buildings beautiful for a long time.



High Durability

With special synthetic resin and ceramic materials, it achieves high durability and weather resistance.



High Adhesive Strength

GRANI PALACE provides excellent adhesion to walls over a long period of time.



Mildew and Algae Resistance


Thanks to the unique formulation, this product prevents contamination by microorganisms such as mildew and algae for a long time, and keeps a hygienic environment.

- Uses
Ordinary exterior walls
- Suitable Substrates
Concrete, cement rendering, various ceramic siding boards



Standard Colours

Shooting Star Patterns



PAG-301



PAG-302



PAG-303



PAG-304



PAG-305



PAG-306



PAG-307



PAG-308

The above printed pictures may be slightly different from actual colours.
Confirm colours by a sample panel before placing an order.

Standard Application Specification

WITHOUT GROOVES

(20°C, 65% RH)

Process	Material	Dilution ratio (wt.%)	Consumption (kg/m ²)	No. of coat	Interval (hr)			Remarks
					In process	Between processes	Final curing	
Surface treatment	<ul style="list-style-type: none"> •Dry the surface completely to bring water content to a maximum 10% and pH to 10 or less. •Completely remove any dirt, dust and make good unevenness, irregularities, and scratches. 							—
Undercoat	ELEGANSTONE #200 ※Same colour as Mid coat	100	1.3-1.7	1	—	30min or less	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle tip: 4-5.5mm Pressure: 490-686kPa(5-7kgf/cm ²)
	WATER	0-5	—					
Mid-coat	GRANI PALACE MID-COAT	100	2.8-3.2	1	—	16 or more	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle size: 4-5.5mm Pressure: 490-686kPa (5-7kgf/cm ²)
	WATER	0-3	—					
Main coat	GRANI PALACE MAIN COAT	Pre-mixed	0.35-0.50	1	—	16 or more	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle size: 5.5mm Pressure: 392-588kPa (4-6kgf/cm ²)
Topcoat	SK ACRYLIC CLEAR TOP W	100	0.20-0.25	2	2 or more	—	24 or more	Roller, Brush Airless spray gun Discharge: 800-1000ml/min. Pattern width: 25-30cm
	WATER	0-20	—					

ONE DECK FINISH

(20°C, 65% RH)

Process	Material	Dilution ratio (wt.%)	Consumption (kg/m ²)	No. of coat	Interval (hr)			Remarks
					In process	Between processes	Final curing	
Surface treatment	<ul style="list-style-type: none"> •Dry the surface completely to bring water content to a maximum 10% and pH to 10 or less. •Completely remove any dirt, dust and make good unevenness, irregularities, and scratches. 							—
Undercoat for grooves	JOINT UNDER COAT	100	0.20-0.25	1-2	2 or more	2 or more	—	Roller, Brush Airless spray gun Discharge: 600-1000ml/min. Pattern width: 25-30cm
	WATER	5-15	—					
Marking for grooves	Mark reference lines for groove designs.				—	—	—	—
Fixing pattern paper	Fix JOINT STICKER L precisely along the reference lines.				—	—	—	—
Undercoat for Mid-coat	ELEGANSTONE #200 ※Same colour as Mid coat	100	1.3-1.7	1	—	30min or less	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle tip: 4-5.5mm Pressure: 490-686kPa (5-7kgf/cm ²)
	WATER	0-5	—					
Mid-coat	GRANI PALACE MID-COAT	100	2.8-3.2	1	—	20min or less	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle size: 4-5.5mm Pressure: 490-686kPa (5-7kgf/cm ²)
	WATER	0-3	—					
Treatment	Remove backing paper promptly.				—	16 or more	—	—
Main coat	GRANI PALACE MAIN COAT	Pre-mixed	0.35-0.50	1	—	16 or more	—	SK ALMIGHTY GUN (Lithin-tip) Nozzle size: 5.5mm Pressure: 392-588kPa (4-6kgf/cm ²)
Removing joint	Remove the core of JOINT STICKER L after main coat is completely cured.				—	—	—	—
Topcoat	SK ACRYLIC CLEAR TOP W	100	0.20-0.25	2	2 or more	—	24 or more	Roller, Brush Airless spray gun Discharge: 800-1000ml/min. Pattern width: 25-30cm
	WATER	0-20	—					

Packing Style

JOINT UNDER COAT	16kg / can
ELEGANSTONE #200	25kg / can
GRANI PALACE MID-COAT	20kg / can
GRANI PALACE MAIN COAT	16kg / can
SK ACRYLIC CLEAR TOP W	15kg / can

※ The above products and application specification may be changed without notice.

Hazards Information and Safety Precautions

Read cautions written on containers thoroughly before use.
Refer to SDS (Safety Data Sheet) for the details.



HEAD OFFICE IN JAPAN

SK KAKEN CO., LTD.

5-25, 3-Chome, Nakahozumi, Ibaraki-City, Osaka, 567-0034, Japan
Tel: (81-72)621-7727 Fax: (81-72)621-7728
Web: <http://www.sk-kaken.co.jp>



SINGAPORE

SKK (S) PTE. LTD.

14 Pandan Road, Singapore 609262
Tel: (65)6274-0020 Fax: (65)6278-0060
Web: <http://www.sk.com.sg>

Factory : SKK (S) PTE. LTD. FACTORY

INDIA

SKK (S) PTE. LTD. BANGALORE BRANCH OFFICE

No.33/5, Mount Kailash, Meance Avenue Road, Ulsoor, Bangalore, 560 042, India
Tel: (91)80-4148-2831 Fax: (91)80-4148-2836

SKK (S) PTE. LTD. DELHI BRANCH OFFICE

55 Community Center, 1st Floor, East of Kailash, New Delhi-110066, India
Tel: (91)11-4654-1999 Fax: (91)11-4654-1998

SKK (S) PTE. LTD. MUMBAI BRANCH OFFICE

Unit No. 2/3, Ground Floor, Neelam Centre, "B" Wing, Hind Cycle Road, Worli, Mumbai- 400 030, India
Tel: (91)22-6743-2528 Fax: (91)22-6743-2524

SKK (S) PTE. LTD. KOLKATA LIAISON OFFICE

1/A, Mahindra Roy lane, Top Sia Road Bypass, Kolkata 700046, West Bengal, India

INDONESIA

SKK (S) PTE. LTD. JAKARTA REPRESENTATIVE OFFICE

Seriabudi Atrium Building, 5th floor, suite 504, Jl. H. R. Rasuna Said Kav. 62, Jakarta, Indonesia 12920
Tel: (62)21-5210401(5210402) Fax: (62)21-5210403

VIETNAM

SKK VIETNAM CO., LTD.

HCMC OFFICE

Unit A1, 1th Floor, Y Ban Building, 69 Phach Thi Thanh St., Tan Dinh Ward, Dist.1, HCMC, Vietnam
Tel: (84)8-2220-0983 Fax: (84)8-2220-0987

HANOI OFFICE

Floor 7, Lotus Building, No.2 Duy Tan Street, Dich Vong Hau Ward, Cau Giay District, Ha Noi city, Vietnam
Tel: (84)4-3556-1151(1152) Fax: (84)4-3556-1153

HONG KONG

SKK (HK) CO., LTD.

The Whole of 38th Floor, @Convoy,
169 Electric Road, Fortress Hill, Hong Kong
Tel: (852)2529-3968 Fax: (852)2527-0299
Web: <http://www.sk.hk.com.hk>

MALAYSIA

SK KAKEN (M) SDN. BHD.

Suite 13.01, Level 13, Centrepoint South, The Boulevard, Mid Valley City, Lingkaran Syed Putra, 59200 Kuala Lumpur, Malaysia
Tel: (60)3-2282-9800 Fax: (60)3-2282-9810
Web: <http://www.sk.com.my>

Branch Office : Johor Bahru, Kuantan, Penang

Factory : SKK CHEMICAL (M) SDN. BHD.

THAILAND

SK KAKEN (THAILAND) CO., LTD.

161/1 SG Tower 5th Floor, Soi Mahadlek Luang 3, Ratchadamri Rd, Lumpini, Pathumwan, Bangkok 10330, Thailand
Tel: (66)2-651-8722 Fax: (66)2-651-8721
Web: <http://www.sk.co.th/>

Branch Office : Chiang mai

Factory : SKK CHEMICAL (THAILAND) CO., LTD.

KOREA

SKK KAKEN (KOREA) CO., LTD.

#301, YeokSam Venture Bldg, 708-33, YeokSam-Dong, GangNam-Gu, Seoul, 135919, Korea
Tel: (82)2-562-1592 Fax: (82)2-562-1594
Web: <http://www.sk-kaken.com>

Branch Office : Busan

Factory : SEOUL FACTORY

CHINA

SIKOKU KAKEN (SHANGHAI) CO., LTD.

Units 3-7, 25F, Far East International Plaza A, No.319 Xianxia Road, Changning District, Shanghai, China
Tel: (86)21-6209-9169 Fax: (86)21-6209-9189
Web: <http://www.sk.com.cn>

Branch Office : Beijing, Guangzhou, Shenyang, Dalian, Wuhan, Tianjin, Changchun, Xi'an, Chongqing, Kunming, Nanjing, Suzhou, Hangzhou, Hefei, Henan, Taiyuan

Factory :

SHANGHAI FACTORY

SIKOKU KAKEN (LANGFANG) CO., LTD.